



HIGH PERFORMANCE 2:1 EPOXY SYSTEM

Pump Instructions


These instructions are for using the TotalBoat calibrated pumps to measure the correct mix ratio of resin to hardener. To ensure the proper mix ratio, do not use any other pumps with these products.

Dispense only **1** pump of RESIN to **1** pump of HARDENER



1 ID YOUR MATERIALS

RESIN PUMP
(no dot)
Dispenses 20cc




Pump Extender 

Use with:

- TotalBoat High Performance 2:1 Epoxy Resin



HARDENER PUMP
(w/ black 2:1 dot)
Dispenses 10cc



Pump Extender 

Use with:


- TotalBoat High Performance 2:1 Hardeners

2 SET UP AND INSTALL YOUR PUMPS

For all sizes of resin, attach the Pump Extender to the white plunger; for the hardener, only attach the extender to the quart and 1/2-gallon pumps —DO NOT attach the extender tube to pump for the pint sized hardener. Trim the pumps using an angled cut, as shown below. Cutting length is indicated from the BOTTOM of the tube. Initially, both pumps are the length to be used with GALLON containers. After trimming, insert the plunger as deeply as possible, without physically touching the bottom.


RESIN PUMP

- Group Size A — Trim by 3-7/8"
- Group Size B — Do not trim
- Group Size C — Do not trim



HARDENER PUMP

- Group Size A — Cut at an angle at the very bottom of pump
- Group Size B — Trim by 2"
- Group Size C — Do not trim



3 PRIME YOUR PUMPS

Before dispensing, push down and release the head of each pump several times until you get a steady stream of liquid, without any air pockets.

4 DISPENSE AND MIX YOUR EPOXY

Dispense the resin and hardener into a clean, dry container that is appropriate for mixing epoxy. For every 1 full pump of resin, dispense 1 full pump of hardener. Mix THOROUGHLY for 2-3 minutes, taking care to scrape the sides and bottom of the container to blend the mixture completely. Do not adjust mix ratios or tamper with pumps. A proper cure is dependent on using the exact recommended mix ratio. Adding more hardener to make the epoxy set faster will actually prevent it from curing properly.



REMEMBER: Dispense only 1 PUMP OF RESIN to 1 PUMP OF HARDENER



Scan this code for additional information and instructions on the TotalBoat High Performance 2:1 Epoxy System